



ACADIAN INDUSTRIAL TEXTILES
TRAMPOLINE FABRIC
3 X 4 BASKETWEAVE
STYLE #52419

Specifications

FIBER CONTENT	100% Virgin Polypropylene
CONSTRUCTION	60 x 50
WEIGHT ASTM D-3776	7.6 oz./yd ²
TENSILE STRENGTH ASTM D-4632, Grab Method	Warp: 440 lbs Fill: 365 lbs
ELONGATION ASTM D-4632, Grab Method	Warp: 23% Fill: 18%
BURST STRENGTH ASTM D-3786	710 lbs/in ²
PUNCTURE STRENGTH ASTM D-4833 Modified	165 lbs
TEAR STRENGTH ASTM D-2261, Trap Method	Warp: 185 lbs Fill: 165 lbs

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee expressed or implied is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.