ACADIAN
INDUSTRIAL TEXTILES

WHITE KNITTED HDPE SHADE FABRIC SPECIFICATIONS

Style #	16750W	16770W
SHADE	40%	50%
WEIGHT (ASTM D-5262)	4.6 oz/yd^2	6.6 oz/yd^2
TENSILE STRENGTH (ASTM D-4632, Grab Method)	Warp: 107 lbs Fill: 127 lbs	Warp: 148 lbs Fill: 209 lbs
ELONGATION (ASTM D-4632, Grab Method)	Warp: 36% Fill: 62%	Warp: 52% Fill: 65%
PUNCTURE STRENGTH (ASTM D-4833)	80 lbs	106 lbs
TEAR STRENGTH (ASTM D-4533)	Warp: 54 lbs Fill: 58 lbs	Warp: 73 lbs Fill: 77 lbs
BURST STRENGTH (ASTM D-3786)	306 psi	461 psi

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee expressed or implied is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.
Product specifications are typical average values and are subject to change.

U.V. INHIBITOR: HALS
TECHNICAL DATA PROVIDED BY PRODUCING MILL & SGI TESTING